



## PLAY PREMIUM

The consistency of this artificial grass play surface helps eliminate common playtime injuries. With built-in Super Yarn™ Technology, this playground turf gives parents peace of mind allowing kids to run, play and roll around, all while maintaining its natural appearance.



### SUPER YARN™ TECHNOLOGY

**SANITIZED®**  
ANTIMICROBIAL

**DUALCHILL™**  
IR REFLECTIVE

**STATBLOCK™**  
ANTI-STATIC

SKU	ST343_PLAY
Grass Zone Yarn/Color	PE / Field Green / Apple
Grass Zone Denier	10,800 / 6
Thatch Zone Yarn/Color	PE / Field Green / Beige
Thatch Zone Denier	5,000 / 8
Grass Zone Yarn Shape	Omega
Finished Pile Height	1 1/2"
Finished Pile Weight	80 oz.
Backing	13PP/18PET 2pt / 22oz. EnviroLoc+™
Tuft Gauge	3/8"
Total Weight	108 oz.
Tuft Bind	> 8 lbs.
Permeability	> 1,000 inches p/hr
Features	Sanitized®, EnviroLoc+™, StatBlock™ Anti-Static, DualChill™ IR Reflective, SuperDrain+™, Deluster, UV Stabilizers
Test Data	ASTM E108 CLASS A FIRE, D2859, EN71, F1292, F1951, RCRA 8 TCLP, CAL 1350, IPEMA



LIMITED LIFETIME WARRANTY\*



OPTIMAL DRAINAGE > 1,000" P/HR




USE IN ALL CLIMATES AND REGIONS



IDEAL FOR ALL PLAY APPLICATIONS

ASK ABOUT OUR...

**USDA CERTIFIED ORGANIC INFILL SYSTEM**



**USDA CERTIFIED BIOBASED PRODUCT**  
PRODUCT 72%

SYNTipede X43 is a USDA Certified Bio-Based artificial grass system in combination with organic infill, able to display a unique USDA label highlighting its percentage of biobased content.





Primary Yarn Polymer	Polyethylene	Primary Backing	13PP/18PET 2pt
Yarn Cross Section	Omega	Coating Type	22 oz. EnviroLoc+
Standard Color	Field Green / Apple	PE Yarn Denier / Ends	10,800 / 6
Fabric Construction	Tufted	Texturized Thatch Denier / Ends	5,000 / 8
Second Yarn Polymer Thatch	Polyethylene	Warranty Period	Limited Lifetime
Secondary Yarn Color	Field Green / Beige		

FINISH FABRIC	ENGLISH SYSTEM		ASTM TEST
	Nominal Specification	Value	Units
Pile Height (Nominal)	1 1/2	inches	D-5823
Face Weight	80	oz/yd <sup>2</sup>	D-5848
Total Fabric Weight	108	oz/yd <sup>2</sup>	D-5848
Primary Backing Weight	6	oz/yd <sup>2</sup>	D-5848
Secondary Coating Weight	22	oz/yd <sup>2</sup>	D-5848
Tuft Bind	> 8	lbs.	D-1335
Grab Tear Strength (Average)	> 200	lbs.	D-5034
Total Yarn Linear Density	15,800	Denier	D-1577
Elongation to Break	> 30	%	D-2256
Yarn Breaking Strength	> 20	lbs.	D-5793
Machine Gauge	3/8	inches	D-5793
Flammability	Passed	-	D-2859
Water Permeability	> 1,000	in/hr	D-1551
Fabric Width	15	ft	-

